



Steel Wire Rope 6x7-WSC

Product information



Rope construction: 6x7-WSC (7x7)

Marking: According to standard

Temperature range: -40°C up to +200°C, for operating temperatures between 100 °C and 200 °C reduce MBF by minus 10 %

Standard: EN 12385-4

Fill factor: 0,55

Stay rope



Agriculture and livestock



General use



Part Code	Rope Diameter, mm	Tensile strength N/mm ²	Finish	Rope lay.	Min. Breaking force, kN	Steel area mm ²	Lubrication	Weight kg/100m	Delivery time
101100204250160	2	1,770	Galvanized	sZ	2.75	1.73	Dry	1.54	2
101100304250160	3	1,770	Galvanized	sZ	6.18	3.89	Dry	3.46	20
101100404250160	4	1,770	Galvanized	sZ	11	6.91	Dry	6.14	2
101100504250160	5	1,770	Galvanized	sZ	17.2	10.8	Dry	9.6	20
101100604250160	6	1,770	Galvanized	sZ	24.7	15.6	Dry	13.8	20