



## Steel Wire Rope 6x24-7FC

### Product information



**Rope construction:** 6x24-7FC.

**Marking:** According to standard

**Standard:** EN 12385-4

**Fill factor:** 0.41

Slings



Part Code	Rope Diameter, mm	Tensile strength N/mm <sup>2</sup>	Finish	Rope lay.	Min. Breaking force, kN	Steel area mm <sup>2</sup>	Lubrication	Weight kg/100m	Delivery time
101100604250310	6	1,770	Galvanized	sZ	17.9	11.6	Dry	11	7
101100804250310	8	1,770	Galvanized	sZ	31.8	20.6	Dry	20	7
101101004250310	10	1,770	Galvanized	sZ	49.6	32.2	Dry	32	7
101101204250310	12	1,770	Galvanized	sZ	71.4	46.4	Dry	46	7
101101404250310	14	1,770	Galvanized	sZ	97.2	63.1	Dry	62	7
101101604250310	16	1,770	Galvanized	sZ	127	82.4	Dry	81	7
101101804250310	18	1,770	Galvanized	sZ	161	104	Dry	103	7
101102004250310	20	1,770	Galvanized	sZ	198	129	Dry	127	7
101102204250310	22	1,770	Galvanized	sZ	240	156	Dry	154	7